

AMENDMENTS TO THE CLAIMS

This listing of claims replaces all prior listing of claims for the present application.

Claims 1-31 (Canceled).

32. (Currently amended) A method of forming a capacitor in a semiconductor device, said method comprising:

forming a bottom conducting layer, wherein said bottom conducting layer forms a bottom electrode;

forming a dielectric layer over the bottom conducting layer;

forming a top ~~conducting layer~~ electrode that consists of a single top conducting layer over the dielectric layer, ~~wherein said top conducting layer forms a top electrode;~~ and

annealing the single top conducting layer of the top electrode with an oxidizing gas anneal.

33. (Original) A method of forming a capacitor of claim 32, wherein said capacitor is formed over a conductive plug, said method further comprising depositing an oxygen barrier over said conductive plug prior to forming the bottom conducting layer.

34. (Original) A method of forming a capacitor of claim 32, said method further comprising: annealing the dielectric layer after it is formed.

35. (Original) A method of forming a capacitor of claim 32, wherein said bottom conducting layer is formed of a material selected from the noble metal group.

36. (Original) A method of forming a capacitor of claim 32, wherein said bottom conducting layer is formed of a metal.

37. (Original) A method of forming a capacitor of claim 32, wherein said bottom conducting layer is formed of a metal alloy.

38. (Original) A method of forming a capacitor of claim 32, wherein said bottom conducting layer is formed of a conducting metal oxide.

39. (Original) A method of forming a capacitor of claim 32, wherein said bottom conducting layer is formed of a metal nitride.

40. (Original) A method of forming a capacitor of claim 32, wherein said bottom conducting layer is formed of a material selected from the group consisting of: Platinum (Pt), Platinum Rhodium (PtRh), Platinum Iridium (PtIr), Ruthenium, Ruthenium Oxide (RuO₂), Rhodium Oxide (RhO₂), Chromium Oxide (CrO₂), Molybdenum Oxide (MoO₂), Rhemium Oxide (ReO₃), Iridium Oxide (IrO₂), Titanium Oxides (TiO₁ or TiO₂), Vanadium Oxides (VO₁ or VO₂), Niobium Oxides (NbO₁ or NbO₂), and Tungsten Nitride (WN_x, WN or W₂N).

41. (Original) A method of forming a capacitor of claim 40, wherein said bottom conducting layer is formed of a material selected from the group consisting of: Platinum (Pt), Platinum Rhodium (PtRh), Platinum Iridium (PtIr), and Tungsten Nitride (WN_x, WN or W₂N).

42. (Original) A method of forming a capacitor of claim 32, wherein said dielectric layer is a dielectric metal oxide layer.

43. (Original) A method of forming a capacitor of claim 32, wherein said dielectric layer has a dielectric constant between 7 and 300.

44. (Original) A method of forming a capacitor of claim 32, wherein said dielectric layer is formed of a material selected from the group consisting of: Tantalum Oxide, Tantalum Pentoxide (Ta_2O_5), Barium Strontium Titanate (BST), Aluminum Oxide (Al_2O_3), Zirconium Oxide (ZrO_2), Praseodymium Oxide (PrO_2), Tungsten Oxide (WO_3), Niobium Pentoxide (Nb_2O_5), Strontium Bismuth Tantalate (SBT), Hafnium Oxide (HfO_2), Hafnium Silicate, Lanthanum Oxide (La_2O_3), Yttrium Oxide (Y_2O_3), and Zirconium Silicate.

45. (Original) A method of forming a capacitor of claim 44, wherein said dielectric layer is formed of a material selected from the group consisting of: Tantalum Oxide, Tantalum Pentoxide (Ta_2O_5), Barium Strontium Titanate (BST), Strontium Bismuth Tantalate (BST), Aluminum Oxide (Al_2O_3), Zirconium Oxide (ZrO_2) and Hafnium Oxide (HfO_2).

46. (Original) A method of forming a capacitor of claim 45, wherein said dielectric layer is Tantalum Oxide and is crystalline or amorphous material.

47. (Previously presented) A method of forming a capacitor of claim 45, wherein said dielectric layer is an amorphous dielectric layer which is heated to a temperature above 200 degrees Celsius to change said dielectric layer from an amorphous material to a crystalline material.

48. (Original) A method of forming a capacitor of claim 32, wherein said top conducting layer is formed of a material selected from the noble metal group.

49. (Original) A method of forming a capacitor of claim 32, wherein said top conducting layer is formed of a non-oxidizing metal permeable to oxygen.

50. (Original) A method of forming a capacitor of claim 32, wherein said top conducting layer is formed of a conducting metal oxide.

51. (Original) A method of forming a capacitor of claim 32, wherein said top conducting layer is formed of a material selected from the group consisting of: Platinum (Pt), Platinum Rhodium (PtRh), Platinum Iridium (PtIr), Ruthenium, Ruthenium Oxide (RuO_2), Rhodium Oxide (RhO_2), Chromium Oxide (CrO_2), Molybdenum Oxide (MoO_2), Rhemium Oxide (ReO_3), Iridium Oxide (IrO_2), Titanium Oxides (TiO_1 or TiO_2), Vanadium Oxides (VO_1 or VO_2), and Niobium Oxides (NbO_1 or NbO_2).

52. (Original) A method of forming a capacitor of claim 51, wherein said top conducting layer is formed of a material selected from the group consisting of: Platinum (Pt), Platinum Rhodium (PtRh), and Platinum Iridium (PtIr).

53. (Original) A method of forming a capacitor of claim 32, wherein said bottom and top conducting layers are formed of a material selected from the group consisting of: Platinum, Platinum Rhodium (PtRh), or Platinum Indium (PtIr) and said dielectric layer is a layer of Tantalum Oxide.

54. (Original) A method of forming a capacitor of claim 32, wherein said bottom and top conducting layers are formed of a material selected from the group consisting of: Platinum, Platinum Rhodium (PtRh), or Platinum Iridium (PtIr) and said dielectric layer is a layer of Barium Strontium Titanate (BST) or Strontium Bismuth Tantalate (SBT).

55. (Original) A method of forming a capacitor of claim 32, wherein said top conducting layers are formed of a material selected from the group consisting of: Platinum, Platinum Rhodium (PtRh), or Platinum Iridium (PtIr) and said bottom conducting layer is a layer of Tungsten Nitride (WN_x, WN or W₂N) layer and said dielectric layer is a layer of Aluminum Oxide (Al₂O₃).

56. (Canceled).

57. (Currently amended) A method of forming a capacitor of claim ~~[[56]]~~ 32, wherein said annealing is performed with a material selected from the group consisting of: Oxygen (O₂), Ozone (O₃), Nitrous Oxide (N₂O), Nitric Oxide (NO), and water vapor (H₂O).

58. (Original) A method of forming a capacitor of claim 57, wherein said annealing is performed with a gas mixture containing at least one element selected from the group consisting: Oxygen (O₂), Ozone (O₃), Nitrous Oxide (N₂O), Nitric Oxide (NO), and water vapor (H₂O).

59. (Currently amended) A method of forming a capacitor of claim ~~[[56]]~~ 32, wherein said annealing is a plasma enhanced annealing.

60. (Original) A method of forming a capacitor of claim 59, wherein said annealing is a remote plasma enhanced annealing.

61. (Currently amended) A method of forming a capacitor of claim ~~[[56]]~~ 32, wherein said annealing is an ultraviolet light enhanced annealing.

62. (Original) A method of forming a capacitor of claim 32, wherein said annealing is performed at a temperature between 300 and 800 degrees Celsius.

63. (Original) A method of forming a capacitor of claim 62, wherein said annealing is performed at a temperature between 400 and 750 degrees Celsius.

64. (Original) A method of forming a capacitor of claim 32, wherein said annealing is performed at a pressure between 1 and 760 torr.

65. (Original) A method of forming a capacitor of claim 64, wherein said annealing is performed at a pressure between 2 and 660 torr.

66. (Original) A method of forming a capacitor of claim 32, wherein said annealing is performed for between 10 seconds and 60 minutes.

67. (Original) A method of forming a capacitor of claim 66, wherein said annealing is performed for between 10 seconds and 30 minutes.

68. (Original) A method of forming a capacitor of claim 32, wherein said annealing is performed in the presence of an oxygen as with a gas flow rate between 0.01 and 10 liters per second.

Claims 69-96 (Canceled).

97. (Currently amended) A method of forming a capacitor in a semiconductor device, said method comprising:

forming a bottom conducting layer, wherein said bottom conducting layer ~~forms~~ is a bottom electrode;

forming a dielectric layer over the bottom ~~conducting layer~~ electrode;

forming a top electrode over said dielectric layer, said top electrode comprising ~~at least one top conducting layer~~ a bottom and a top conducting layer; and

annealing said ~~at least one~~ top conducting layer of said top electrode with an oxidizing gas anneal.